

# KAPPAZON K 75-250

## Peroxide stabilizer

Chemical composition	combination of inorganic and organic salts
Appearance	yellow-brown, clear solution
pH-value 20 °C	5.0 - 6.5 (product)
Density 20 °C (g/ml)	approx. 1.1
Ionic charge	anionic

## Function

KAPPAZON K 75-250

- is an universally applicable stabilizer for the bleaching of cellulosic fibres with hydrogen peroxide.
- is effective independent from the water hardness.
- has no interfacial-active properties and therefore is foam-free.

## Application

Bleaching of cotton fabric on the jig:

The desized or scoured fabric is treated with the following liquor:

- 0.3 – 0.4 ml/l KAPPAZON K 75-250
- 6.0 ml/l NaOH 38 °Bé
- 10.0 ml/l H<sub>2</sub>O<sub>2</sub> 35 %
- 2.0 g/l wetting agent/detergent, e. g. KAPPAWET BOS
- 6 – 8 passages at 95°C

Bleaching of cotton yarn on the cross wound bobbin:

- 0.1 – 0.2 ml/l KAPPAZON K 75-250
- 3.0 ml/l NaOH 38 °Bé
- 5.0 ml/l H<sub>2</sub>O<sub>2</sub> 35 %
- 0.5 g/l wetting agent/detergent, e. g. KAPPAWET BOS

For full-white, add:

- 0.2 % KAPPAPHOR ME
- 20 minutes from 20 °C – 110 °C
- 45 minutes at 110 °C

Bleaching of cotton tricot on the winch:

- 0.1 ml/l KAPPAZON K 75-250
- 2.0 ml/l NaOH 38 °Bé
- 4.0 ml/l H<sub>2</sub>O<sub>2</sub> 35 %
- 1.0 g/l wetting agent/detergent, e. g. KAPPAWET BOS

For full-white, add:

- 0.2 % KAPPAPHOR ME
- 60 minutes at 95 °C

When using the products, the precautionary measures applicable to the handling of chemicals must be observed. For storage and hazard information as well as safety advice, please refer to the relevant safety data sheets. Application solutions and product residues must be disposed of in accordance with official regulations. The listed instructions correspond to our previous experience. However, in view of the different operating conditions, only non-binding information and advice can be given. Therefore, we cannot accept any liability whatsoever, including liability for claims by third parties. Errors, changes and misprints excepted. Non-binding product information, print date Feb 17, 2022, not subject to systematic change.

## Contact

**KAPP Chemie**  
 info@kapp-chemie.com  
 +49 / 6772 / 9311-0



**KAPP-CHEMIE GmbH & Co. KG**  
 Industriestraße 2-4  
 56357 Miehlen  
 www.kapp-chemie.com

Bleaching in accordance with different padding processes (Cold pad-batch process, pad-roll process, various continuous processes):

Recommended average application level:

- 1.0 – 2.0 ml/l KAPPAZON K 75-250, possibly in combination with
- 5.0 – 10.0 ml/l waterglass 38 °Be

Detailed formulation recommendations on request!

Regarding the application of the additionally mentioned products, please note the corresponding technical data sheets.

### **Dilution instruction**

KAPPAZON K 75-250 can be diluted with cold water at any ratio. The product can be added directly to the bleaching liquor.

### **Storage**

KAPPAZON K 75-250 remains stable for at least 1 year when stored properly and cool in a tightly closed original container.