

KAPPASOFT KB fl

Cationic softener / finishing agent

Chemical composition	fatty acid derivative
Appearance	white, viscous liquid
pH-value 20 °C	approx. 3.0 (prodcut)
Ionic charge	cationic

Contact

KAPP-CHEMIE Textil
 info@kapp-chemie.com
 +49 / 6772 / 9311-0

Function

KAPPASOFT KB FL imparts a glossy, comfortable soft handle to cellulosic and synthetic fibres.

KAPPASOFT KB FL

- shows no yellowing
- has antistatic properties
- is particularly suitable for garments
- is easy to handle
- is compatible with nonionic and cationic products

Application

KAPPASOFT KB FL can be used in the continuous as well as in the discontinuous process.

The recommended application level depends on the substrate of textile material and the desired handle:

Padding process

- 10 – 30 g/l KAPPASOFT KB FL

Exhaustion process

- 1.0 – 3.0 % KAPPASOFT KB FL

Garment

- 3,0 – 6,0 % KAPPASOFT KB FL
- Liquor ratio: 1:8
- Treatment time: 15 minutes
- Temperature: 35 °C
- pH-value: approx 5,0 adjust with acetic acid

Centrifuge without rinsing before and dry with tumbler.

Dilution instruction

KAPPASOFT KB FL can be emulsified with cold water at any ratio.

Storage

KAPPASOFT KB FL remains stable for at least 1 year if stored properly at room temperature in a tightly closed container.

Do not expose to frost!

