

# KAPPAPHOB RIW 6

## Fluorocarbon polymer for re-impregnation in washing machine

Chemical composition	fluorocarbon polymer in aqueous solution
Appearance	white emulsion
pH-value 20 °C	approx. 6.3 (product)
Density 20 °C (g/ml)	approx. 1.0
Ionic charge	nonionic

### Function

KAPPAPHOB RIW 6 is a special developed fluorocarbon polymer emulsion for re-impregnation in the washing machine. Textiles made of different materials such as outdoor jackets, backpacks, tents, etc. can be impregnated in the washing machine to regain water- and soil repellency. The product does not contain any verifiable perfluoro octane acids, perfluoro octane sulfonic acids or other parts of a perfluorinated chain length over 6 C-atoms.

### Application

The textiles have to be washed according to the care instruction in order to achieve an optimum effect.

#### Instructions:

- Clean detergent box of detergent residues.
- Put clean textiles (max. 2 pieces) in washing machine.
- Do not add detergent.
- Dose 100 ml KAPPAPHOB RIW 6 per article in the box for softeners.
- Turn on the program "easy to clean" at 30 °C, 400 – 600 spin-dry.
- Dry the re-impregnated textile in the air.

A heat treatment with a tumbler increases the effect (30 minutes at approx. 50 °C). Iron according care instruction could increase the effect as well.

### Storage

KAPPAPHOB RIW 6 remains stable for at least 6 months if stored properly and cool in a tightly closed original container.

Do not expose to frost!

### Contact

**KAPP Chemie**  
info@kapp-chemie.com  
+49 / 6772 / 9311-0

