

KAPPASOFT FAP

Lubricant for yarn

Chemical composition	preparation of modified wax emulsions
Appearance	white-beige emulsion
pH-value 20 °C	approx. 4.5 (product)
Density 20 °C (g/ml)	approx. 1.0
Ionic charge	weakly cationic

Function

KAPPASOFT FAP was especially developed for natural and synthetic fibres, yarns and filaments to improve the gliding properties. The product has an excellent affinity to the substrates.

KAPPASOFT FAP

- provides low friction coefficients.
- results in optimal gliding properties.
- improves the sewability.
- is compatible with cationic and nonionic products.
- is not compatible with anionic products.
- is resistant to acids and hard water.
- is not resistant to alkali and electrolytes.
- does not cause yellowing of the fibre material even at temperatures up to 170 °C.
- does not cause yellowing during storage.

Application

Recommended application levels:

Exhaustion process

- 2.0 – 4.0 % KAPPASOFT FAP
- pH-value: 5.0 – 6.0
- Liquor temperature: 55 °C
- Treatment time: 30 minutes
- Drying at: 110 – 150 °C

Dilution instruction

KAPPASOFT FAP can be emulsified with cold water at any ratio.

Storage

KAPPASOFT FAP remains stable for at least 6 months if stored properly and at room temperature in a tightly closed container.

Protect against frost!

Contact

KAPP Chemie
 info@kapp-chemie.com
 +49 / 6772 / 9311-0

